



Chenming GmbH
THERMAL PAPER 58g

Specifications

Property	Tolerance	Value	Standard
Grammage (g/m ²)	+ 2	58	
Thickness (μm)	+ 4	61	
Bulk (cm ³ /g)		1.08	
Brightness (%)		≥ 85	
Dynamic Response Fourth Lattice (mj/mm ²)		≥ 0.75	
Dynamic Response Sixth Lattice (mj/mm ²)		≥ 1.2	
Smoothness first (s)		≥ 250	
Roughness (μm)		≤ 2.0	
Tension (N)		≥ 2.5	
Keep period (year)		one year	